

NOVA Chemicals® Expandable Polystyrene Resins

Product Data Sheet

Insulation, SIP's, Fabricated Packaging

M77BLV

Features/Attributes:

- Low Pentane
- Reduced Prepuff Age Times
- Fast Molding Cycles
- Controlled/Uniform Expansion

Applications:

- Insulation
- SIP's
- Fabricated Packaging

| Properties | Typical Values (English Units) | Typical Values (S.I. Units) | |
|---|---|--|--|
| Product Properties: | | | |
| (B) Bead Size – avg. bead size diameter | 0.033 inches | 0.85 millimeter | |
| Pentane Content (Avg.) | 4.5% by weight | 4.5% by weight | |
| Bulk Density | 38 – 40 pounds per cubic foot | 608 – 640 grams per liter | |
| Thermal Properties: | | | |
| Thermal Resistance (R-Value) | 3.9- 4.2 per inch | - | |
| Thermal Conductivity ¹ (K-factor, Lambda) Foot (ft) British Thermal Unit (Btu) Degree Fahrenheit (°F) Degree Centigrade (°C) | 0.240-0.210 Btu-in/(hr-ft ² -°F) | 34.5-30.2 milli-Watts/(meters-° Kelvin) | |
| Coefficient of Linear Expansion Inch (in) Centimeter (cm) | 3.5 x 10 ⁻⁵ in/in/° F | 6.3 cm/cm/° C | |
| Maximum Continuous Service Temperature | 175° F | 80° C | |

¹ The thermal conductivity of expanded polystyrene at an average temperature of 75°F (24°C) is lowest at 3.5 pounds per cubic foot (pcf). It rises slightly at lower density until about 1.5 pcf where it increases rapidly. The rate of increase is much less at higher densities:

8.0 pcf (128 g/l) \rightarrow 0.269 Btu-in/(hr-ft²-°F) or 38.7 mW/(m-K) 12.0 pcf (192 g/l) \rightarrow 0.276 Btu-in/(hr-ft2-°F) or 39.8 mW/(m-K)

M77BLV

NOVA Chemicals® EPS



Availability

NOVA Chemicals® expandable polystyrene (EPS) resins are produced at the Beaver Valley plant site (Monaca, PA) and are available in 2205 pound (1 metric tonne) bulk bags. The product type and batch number are clearly marked on each bag. Contact the NOVA Chemicals sales office in your region.

Quality and Environmental Management Systems

M77BLV resins are manufactured at an ISO 9001 and ISO 14001 registered facility.

Storage and Handling

M77BLV should be stored in a cool, dry place away from direct sunlight. This product can release pentane during expansion and molding. Pentane is a highly flammable gas in the presence of open flames, lit cigarettes, sparks, static electricity discharges, or heat. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals' Material Safety Data Sheet (MSDS) and EPS Storage and Handling Safety Guide contain important safety information and should be reviewed before using the product. These and additional safety and health information are available on our Product Care webpage.

Processing Conditions

Recommended Conditions:

Minimum Density:

Batch pre-expander:

• 0.90 pounds per cubic foot or 14.4 grams per liter

Continuous pre-expander:

• 1.20 pounds per cubic foot or 19.2 grams per liter

Pre-puff age time:

8-48 hours – depending on pre-expanded density and method of bead pre-expansion.

Comprehensive assistance with processing conditions and Technical Services are available from NOVA Chemicals Styrenics Technology Center.

Environmental Information

NOVA Chemicals® EPS resins are biologically and chemically inert. NOVA Chemicals® EPS resins does not contain CFC's (Chlorofluorocarbons). NOVA Chemicals® EPS resins are recyclable.

is the SPI resin code for polystyrene to identify material type for sorting and recycling. Significant information regarding EPS recycling is available from the Alliance of Foam Packaging Recyclers. Where recycling of EPS resins is not possible, disposal to landfill or incineration in accordance with applicable laws and regulations is recommended. Contact NOVA Chemicals Styrenics Technology Center for further information on recycling and disposal.

NOVA Chemicals® is a proud member of EPS Industry Alliance. For additional EPS information please visit: http://epsindustry.org/

ICC-ES Evaluation Report – ESR 1798

http://www.icc-es.org/reports/pdf_files/ICC-ES/ESR-1798.pdf

UL Listings

http://database.ul.com/cgibin/XYV/template/LISEXT/1FRAME/index.html

Construction File number R4775

www.novachemicals.com

EPS Sales and Manufacturing

NOVA Chemicals, Inc.

400 Frankfort Road Monaca, PA 15061 Phone: 724.774.1000 Fax: 724.770.6701

Latin America Sales

Telephone: 786.242.1375 Fax: 519.862.7215

Asia and Pacific Rim Sales Office

NOVA Chemicals (International) S.A.

Level 15 Prudential Tower 30 Cecil Street Singapore 049712 Phone: 65.6224.8807 Fax: 65.6224.1877


Technical Center

NOVA Chemicals
Performance Styrenics
Technology Center
400 Frankfort Road


Monaca, PA 15061 Phone: 724.774.1000 Fax: 724.770.5601 M77BLV

NOVA Chemicals® EPS

TYPICAL MECHANICAL PROPERTIES:




Flexural Strength - Pounds per square inch (psi) and Density – Pounds per Cubic Foot (pcf).



M77BLV

NOVA Chemicals® EPS



Water Absorption MIL-P-19644

| Lbs of Water Absorbed per sq. ft. of Specimen Surface. | | | Kg of Water Absorbe sq. meter of Specime | - | | | |
|--|-----------------|--------|---|--------|---------------|---------|--|
| Nomi | Nominal Density | | | | | | |
| pcf | kg/m³ | Actual | Specification | Actual | Specification | % By | |
| | | | Max | | Max | Voliume | |
| 1.0 | 16 | 0.05 | 0.12 | 0.24 | - | 2.8 | |
| 1.5 | 24 | 0.04 | - | 0.20 | - | 2.3 | |
| 2.0 | 32 | 0.04 | 0.12 | 0.20 | 0.59 | 2.3 | |
| 2.5 | 40 | 0.04 | - | 0.20 | - | 2.3 | |
| 3.0 | 48 | 0.04 | 0.12 | 0.20 | 0.59 | 2.3 | |
| 5.0 | 80 | 0.03 | 0.10 | 0.15 | 0.49 | 1.7 | |



NOVA Chemicals® EPS

Water Vapor Permeability ASTM C-355

| Nominal Density | | Perm-In. | | Perm-Cm. | |
|-----------------|---------|----------|---------|----------|---------|
| pcf | Fusion | Plaques | Blocks | Plaques | Blocks |
| 1.0 | Optimum | 1.0-2.0 | 1.5-3.0 | 1.5-3.5 | 2.0-5.0 |
| 1.4 | Optimum | 0.5-2.0 | 1.5-3.0 | 1.5-3.0 | 2.0-5.0 |
| 2.2 | Optimum | 0.5-1.5 | 1.0-2.5 | 1.0-2.5 | 2.0-4.0 |
| 2.5 | Optimum | 0.5-1.5 | 1.0-2.5 | 1.0-2.5 | 1.5-4.0 |
| 1.0 | Minimum | 1.5-3.0 | 2.0-3.5 | 2.5-5.0 | 2.5-6.0 |
| 2.3 | Minimum | 1.0-2.0 | 1.5-3.0 | 1.5-3.5 | 2.5-5.0 |

Thermal Conductivity, k, vs Density Mean Temperature 75°F (24°C) ASTM C-518

| | Density (pcf) | | | | |
|------------------|---------------|------|------|------|------|
| Units | 1.0 | 1.25 | 1.5 | 2.0 | 2.5 |
| Btu in./hr-ft-°F | .255 | .244 | .242 | .239 | .235 |

The product properties in the data sheet have been determined in accordance with the current testing methods of the American Society for Testing and Materials (ASTM), wherever possible.

NOVA Chemicals® is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée DYLITE® is a registered trademark of NOVA Chemicals, Inc.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.