



NOVAPOL® PF-0318-E Resin

Butene Copolymer LLDPE Film Resin

Property	ASTM ⁽¹⁾	Typical Values ⁽²⁾	
Melt Index ⁽³⁾	D 1238	2.7 g/10 min	
Density	D 792	0.919 g/cm ³	
		METRIC UNITS	ENGLISH UNITS
Film Properties⁽⁴⁾			
Thickness		20 µm	0.8 mil
Tear Strength	MD D 1922	57 g	
	TD	369 g	
Low Friction Puncture ⁽⁵⁾		28 J/mm	6 in-lb/mil
Tensile Strength	MD D 882	34 MPa	4,900 psi
	TD	21 MPa	3,000 psi
Yield Strength	MD D 882	9 MPa	1,300 psi
	TD	9 MPa	1,300 psi
Elongation	MD D 882	642 %	642 %
	TD	932 %	932 %
1% Secant Modulus	MD D 882	170 MPa	24,700 psi
	TD	170 MPa	24,700 psi
Haze	D 1003	2 %	2 %
Gloss @ 45°	D 2457	93	93

Melt Index 2.7

Density 0.919

Slip None

Antiblock None

Features

- Excellent optical properties
- Easy processability

Additives

- High temperature AO

Applications

- Cast stretch wrap
- Co-extrusion

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Film properties are typical of cast film extruded at 280°C.

(5) NOVA Chemicals test method.



NOVAPOL PF-0318-E Resin

Butene Copolymer LLDPE Film Resin

Availability

NOVAPOL PF-0318-E polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

NOVAPOL PF-0318-E resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

For regulatory compliance information, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



4 is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.

The NOVA Chemicals logo is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.
NOVAPOL® is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.

November 9, 2017

