

polyethylene

SCLAIR® 2909 Resin

Homopolymer HDPE Injection Molding Resin

product data sheet

Property	ASTM ⁽¹⁾	Typical Values ⁽²⁾	
Melt Index ⁽³⁾	D 1238	13 g/10 min	
Density	D 792	0.962 g/cm ³	
		METRIC UNITS	ENGLISH UNITS
Snake Flow Number		23 cm	9 in
Yield Strength	⁽⁴⁾ D 638	29 MPa	4,200 psi
Elongation	⁽⁴⁾ D 638	800 %	800 %
Flexural Modulus	D 790	1,280 MPa	185,600 psi
Hardness, Shore D	D 2240	65	65
Vicat Softening Point	D 1525	129 °C	264 °F
ESCR, (F ₅₀)	⁽⁵⁾ D 1693	< 10 h	

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Tensile pull speed 50 mm/min.

(5) Environmental stress crack resistance, Condition A, 100% Igepal.

Melt Index 13

Density 0.962

Features

- High stiffness
- Maximum impact strength and toughness
- Good top loading capability
- High surface gloss

Additives

- Processing antioxidant

Applications

- Tote boxes
- Beverage crates

PRODUCT DATA SHEET

SCLAIR 2909 Resin

Homopolymer HDPE Injection Molding Resin

Availability

SCLAIR 2909 polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

SCLAIR 2909 resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: SCLAIR 2909 resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 2.2, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without temperature or food-type restrictions, subject to technical suitability.


Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for high density polyethylene to identify material type for sorting and recycling purposes.

 is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.
SCLAIR® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals (International) S.A. elsewhere; authorized use/utilisation autorisée.

January 5, 2017