

polyethylene



SCLAIR® 8107 Resin

Butene Copolymer LLDPE Injection Molding Resin

| Property | | ASTM (1) | | Туріс | cal Values (2) | |
|---------------------------|-----|----------|---------|-------------|----------------|---|
| Melt Index ⁽³⁾ | | D 1238 | | 4. | .8 g/10 min | |
| Density | | D 792 | | 0.925 g/cm³ | | |
| | | | METRI | C UNITS | ENGLISH UNITS | 3 |
| Yield Strength | (4) | D 638 | 10.5 | MPa | 1,500 psi | |
| Elongation | (4) | D 638 | 850 | % | 850 % | |
| Flexural Modulus | | D 790 | 400 | MPa | 58,000 psi | |
| Hardness, Shore D | | D 2240 | 52 | | 52 | |
| Vicat Softening Point | | D 1525 | 91 | °C | 196 °F | |
| ESCR, (F ₅₀) | (5) | D 1693 | > 1 000 | h | | |

| (1) Properties designated have been | determined using methods w | hich are in accordance with | , or substantially in accordance w | ith, |
|-------------------------------------|----------------------------|-----------------------------|------------------------------------|------|
| the specified testing standards. | | | | |

- (2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.
- (3) Condition 190°C/2.16 kg.
- (4) Tensile pull speed 50 mm/min.
- (5) Environmental stress crack resistance, Condition A, 100% Igepal.

| Melt Index | 4.8 |
|-------------------|-------|
| Density | 0.925 |

Features

- Excellent ESCR
- · Excellent low temperature impact

Additives

Processing antioxidant

Applications

- Automotive
- Food containers
- · Custom molding

polyethylene

PRODUCT DATA SHEET

SCLAIR 8107 Resin

Butene Copolymer LLDPE Injection Molding Resin

Availability

SCLAIR 8107 polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

SCLAIR 8107 resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: SCLAIR 8107 resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without food-type restrictions, under Conditions of Use A–H (21 CFR 176.170(c) Table 2). Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.

▲ NOVA Chemicals' is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

SCLAIR® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals (International) S.A. elsewhere; authorized use/utilisation autorisée.

April 24, 2018



403.291.8444 | 800.222.7213 | info@novachem.com | www.novachemicals.com