



# SCLAIR® FP120 Series Resin

## Octene Copolymer LLDPE Film Resins

**Grades**

FP120-A  
 FP120-C02  
 FP120-CE02  
 FP120-CN  
 FP120-D02  
 FP120-F02

**Additive Packages**

Processing AO only  
 Non-fluorinated PPA  
 Non-fluorinated PPA, enhanced processing AO  
 PPA, gas-fade-resistant processing AO  
 Slip (1000 ppm), AB (2500 ppm), Non-fluorinated PPA  
 AB (3000 ppm), Non-fluorinated PPA

**Applications**

General purpose film, co-extrusion and lamination  
 Food packaging, freezer film, lamination and sealant film  
 Food packaging, freezer film, lamination and sealant film  
 Food packaging, freezer film, lamination and sealant film  
 Food packaging, freezer film, lamination and sealant film  
 Heavy duty shipping sacks, high strength packaging

AO = antioxidant, PPA = polymer process aid, AB = antiblock

Property	ASTM <sup>(1)</sup>	Typical Values <sup>(2)</sup> for FP120-D
Melt Index <sup>(3)</sup>	D 1238	1.0 g/10 min
Density	D 792	0.920 g/cm <sup>3</sup>
		METRIC UNITS      ENGLISH UNITS

**Melt Index 1.0**
**Density 0.920**
**Film Properties<sup>(4)</sup>**

Property	ASTM	Metric Units	English Units
Thickness		25 µm	1.0 mil
Tear Strength	MD D 1922	420 g	
	TD	605 g	
Dart Drop Impact, F <sub>50</sub>	D 1709/A	270 g	
Low Friction Puncture <sup>(5)</sup>		36 J/mm	8 in-lb/mil
Tensile Strength	MD D 882	48 MPa	7,000 psi
	TD	32 MPa	4,600 psi
Yield Strength	MD D 882	10 MPa	1,500 psi
	TD	10 MPa	1,500 psi
Elongation	MD D 882	480 %	480 %
	TD	670 %	670 %
1% Secant Modulus	MD D 882	175 MPa	25,400 psi
	TD	195 MPa	28,300 psi
Haze	D 1003	10 %	10 %
Gloss @ 45°	D 2457	59	59

**Features**

- Easy processability
- High toughness and strength
- Excellent seal properties

**Common Additives**

- Processing antioxidant

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Film properties are typical of blown film extruded on a 2.5" extruder with 4" die and 35-mil die gap at a blow up ratio of 2.5:1, but are dependent upon operating conditions.

(5) NOVA Chemicals test method.



# SCLAIR FP120 Series Resin

## Octene Copolymer LLDPE Film Resins

---

### Availability

SCLAIR FP120 Series polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

### Storage/Handling

SCLAIR FP120 Series resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

### Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

### Food Packaging Status

United States: SCLAIR FP120 Series resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without food-type restrictions, under Conditions of Use A–H (21 CFR 176.170(c) Table 2).

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

### Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



4 is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.

The NOVA Chemicals logo is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

SCLAIR® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals (International) S.A. elsewhere; authorized use/utilisation autorisée.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.

June 13, 2023