


Product Data Sheet

SURPASS® HPx267-AB Resin

Homopolymer HDPE Film Resin

Property	ASTM ⁽¹⁾	Typical Values ⁽²⁾
Melt Index ⁽³⁾	D 1238	2.0 g/10 min
Density	D 792	0.967 g/cm ³
		METRIC UNITS ENGLISH UNITS

Melt Index **2.0**
Density **0.967**

Film Properties⁽⁴⁾

Thickness		38 µm	1.5 mil
Tear Strength	MD D 1922	22 g	
	TD	60 g	
Low Friction Puncture ⁽⁵⁾		23 J/mm	5 in-lb/mil
Yield Strength	MD D 882	30 MPa	4,400 psi
	TD	35 MPa	5,100 psi
1% Secant Modulus	MD D 882	1,050 MPa	152,300 psi
	TD	1,400 MPa	203,100 psi
OTR ⁽⁶⁾	D 3985	372 cm ³ /m ² /day	24 cm ³ /100in ² /day
MVTR ⁽⁷⁾	F 1249	0.9 g/m ² /day	0.06 g/100 in ² /day

Features

- Superior barrier properties
- Very high stiffness
- Low gel

Additives

- Processing antioxidant

Applications

- Moisture barrier films
- Co-extrusion
- Dry food packaging

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Film properties are typical of blown film extruded on a 2.5" extruder with 4" die and 35-mil die gap at a blow up ratio of 2.5:1, but are dependent upon operating conditions.

(5) NOVA Chemicals test method.

(6) Oxygen Transmission Rate, 23°C (74°F), 0% RH, atmospheric pressure.

(7) Moisture Vapour Transmission Rate, 38°C (100°F), 100% RH, atmospheric pressure.



SURPASS HPx267-AB Resin

Homopolymer HDPE Film Resin

Availability

SURPASS HPx267-AB polyethylene resins are available in bulk hopper cars, hopper trucks, or boxes. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

SURPASS HPx267-AB resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: SURPASS HPx267-AB resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 2.2, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without food-type restrictions, under Conditions of Use A–H (21 CFR 176.170(c) Table 2).

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for high density polyethylene to identify material type for sorting and recycling purposes.

The NOVA Chemicals logo is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.

October 27, 2025